


High Temperature Ageing


Condition : +120 °C
Component : QFP100, P0.65mm
PCB Surface : Copper, Pre-flux



Joint strength of SCS7 remain stable after 500hrs of ageing at high temperature condition.

After 1000 hrs High Temperature Ageing:

0805 Chip Capacitor



No abnormalities observed.